



ProFlex® RV Premium Elastomeric Finish Coat White

ProFlex® RV Premium Elastomeric Finish Coat White is formulated using a 100% acrylic polymer that provides outstanding weathering and superior reflectivity properties. Formulated to resist cracking and peeling, ProFlex® RV Premium Elastomeric Finish Coat provides excellent waterproofing capabilities. The bright white finish reduces surface temperatures thereby minimizing thermal expansion and contraction. Under-the-roof temperatures are also reduced.

Basic Uses:

- Refer to ProFlex® RV Fluid Applied Roofing System Specifications for minimum application rates. Application rates and technique vary with substrate system type.

Adheres To: Metal, EPDM, Aged TPO & PVC

Composition and Materials:

Acrylic

Grade:

Self-leveling, brushable grade consistency

Primer:

Not required on most surfaces. If primerless adhesion to a particular substrate is in question, a test application is recommended.

Disclaimer:

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of Geocel® Coatings- A Business Unit of the Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of the publication. Consult your ProFlex® RV Technical Representative to obtain the most recent Product Data Information.

KEEP PRODUCT FROM FREEZING

Installation:

Surface Preparation: For maximum adhesion to heavily oiled or dirty surfaces, areas to be sealed may need to be wiped with a solvent and allowed to dry. Use of a dry rag or brush to remove dust, dirt, or other contaminants is recommended. Contact Geocel Products Group's Technical Service Department or representative if such agents are involved.

Part #	Color	Size	Qty/Cs	UPC	SCC
KSRV41300-16	White	Gallon	4	050926005269	10050926005266

Cleaning:

Warm, soapy water

Cautions:

CONTAINS AROMATIC HYDROCARBONS. Contents are COMBUSTIBLE. Keep away from heat and open flame. VAPOR HARMFUL. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. First Aid: In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. Warning: This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF REACH OF CHILDREN

Availability and Cost:

Available from various RV distributors. Cost and further technical data are available from your local Geocel Products Group

Limited Warranty:

If when applied according to label directions this product fails to perform in accordance with its published literature, Seller and manufacturer's only obligation shall be to replace such quantity of product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential arising from the use or the inability to use the product for his/her intended use, and user assumes all risk and liability. Color fade is not covered under warranty.

Technical Services:

Geocel Products Group representatives throughout the U.S. are available to provide technical assistance. Our in-house technical staff and laboratory facilities are equipped to respond to specific requests for further information.

Typical Physical Properties

Property	Results	Test Method
Vehicle Base	100% Acrylic Resin	
Tensile at Peak (psi)	240	ASTM D 2370
Elongation at Break (%)	180	ASTM D 2370
Tack Free Time	4-6 hours	
Viscosity	110 + 5KU	